

by interplast


ANEX

your partner in chemistry





your partner



INTERPLAST has been one of the leading polyurethane, finish & pigment paste supplier in the synthetic leather market for more than 40 years. Building on its strong presence in the market, Interplast started its own production in 2015 by investing in a modern and highly technological factory. In a short period of time, Interplast has become a leading actor in its region for coating markets

in chemistry

Aliphatic Polyurethanes are excellent topcoat materials defending the leather surface with excellent UV resistance and mechanical resistance, offering stable colors for many years. High compatibility with PVC substrates makes aliphatic polyurethanes even more desirable for vinyl leather applications. When high end performance is required, aliphatic polycarbonate polyurethanes meet the technical expectations of challenging applications such as, automotive and marine industry, combining chemical and mechanical resistance with UV fastness and excellent weatherability.

Aliphatic Polyurethane Resin

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
IPA/TOL Solutions					
ANEX AK 112-30	Aliphatic Topcoat PU	25 ± 1	30	5-10	Alcohol/TOL
ANEX AK 110-30	Aliphatic Topcoat PU	30 ± 1	30	5-10	Alcohol/TOL
ANEX 55	Aliphatic Topcoat PU	25 ± 1	90	15-25	Alcohol/TOL
ANEX AK 1180	Aliphatic Topcoat PU	25 ± 1	180	15-30	Alcohol/TOL
ANEX 51	Aliphatic Topcoat PU	25 ± 1	220	15-25	Alcohol/TOL
ANEX 37	Aliphatic Topcoat PU	25 ± 1	230	15-25	Alcohol/TOL
DMF Solutions					
ANEX 58	Aliphatic Topcoat PU	25 ± 1	50	15-25	DMF
ANEX 54	Aliphatic Topcoat PU	25 ± 1	90	15-25	DMF
PURANEX L 1095/25	Aliphatic Topcoat PU	25 ± 1	95	5-10	DMF
PURANEX L 1100/35	Aliphatic Topcoat PU	35 ± 1	100	5-15	DMF
PURANEX L 1120/25	Aliphatic Topcoat PU	25 ± 1	120	15-25	DMF
ANEX 50	Aliphatic Topcoat PU	25 ± 1	220	15-25	DMF
PURANEX L 1221/25	Aliphatic Topcoat PU	25 ± 1	220	30-60	DMF
ANEX 36	Aliphatic Topcoat PU	25 ± 1	230	15-25	DMF
Mix Solutions					
PURANEX L 3040/30	Aliphatic Topcoat PU	30 ± 1	40	4-8	DMF/TOL/IPA
PURANEX L 3080/25	Aliphatic Topcoat PU	25 ± 1	80	4-8	DMF/TOL/IPA
PURANEX L 3120/25	Aliphatic Topcoat PU	25 ± 1	120	15-30	DMF/TOL/IPA
PURANEX L 3180/25	Aliphatic Topcoat PU	25 ± 1	180	3-6	DMF/TOL/IPA
PURANEX L 3200/30	Aliphatic Topcoat PU	30 ± 1	200	4-8	DMF/TOL/IPA
PURANEX L 3300/25	Aliphatic Topcoat PU	25 ± 1	300	5-10	DMF/TOL/IPA
DMF-Free & TOL-Free Solutions					
PURANEX L 5040/30	Aliphatic Topcoat PU	30 ± 1	40	40-60	DMSO/PMA
ANEX ECO 655	Aliphatic Topcoat PU	25 ± 1	90	15-30	Alcohol/MEK/MA
ECO PU 1103	Aliphatic Topcoat PU	25 ± 1	100	15-30	MSM, PMA
ANEX ECO 651	Aliphatic Topcoat PU	25 ± 1	220	15-30	DMSO/PMA
ANEX ECO 637	Aliphatic Topcoat PU	25 ± 1	230	15-30	DMSO/PMA

Polycarbonate Based

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
IPA/TOL Solution					
ANEX 99	Aliphatic PU Topcoat	25 ± 1	50	15-25	Alcohol/TOL
ANEX 95	Aliphatic PU Topcoat	25 ± 1	90	15-25	Alcohol/TOL
ANEX 91	Aliphatic PU Topcoat	25 ± 1	320	15-25	Alcohol/TOL
DMF Solutions					
ANEX 98	Aliphatic PU Topcoat	25 ± 1	50	15-25	DMF
ANEX 94	Aliphatic PU Topcoat	25 ± 1	90	15-25	DMF
ANEX 90	Aliphatic PU Topcoat	25 ± 1	320	15-25	DMF
Mix Solution					
PURANEX LC 3075/25	Aliphatic PU Topcoat	25 ± 1	75	60-80	DMF/TOL/IPA
PURANEX LC 3200/25	Aliphatic PU Topcoat	25 ± 1	200	10-15	DMF/TOL/IPA
DMF-Free&TOL-Free Solution					
PURANEX LC 5042/25	Aliphatic PU Topcoat	25 ± 1	40	15-30	DMSO/PMA
PURANEX LC 5075/25	Aliphatic PU Topcoat	25 ± 1	75	60-80	DMSO/PMA
ANEX ECO 696	Aliphatic PU Topcoat	25 ± 1	90	15-30	DMSO/PMA
ANEX ECO 691	Aliphatic PU Topcoat	25 ± 1	220	15-30	DMSO/PMA

Special Aliphatic Polyurethanes

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX AS 5030	Aliphatic Topcoat PU with Soft Silky Touch	30 ± 1	30	15-30	DMF
PURANEX LH 5030/40	Aliphatic PU Adhesive	40 ± 1	30	15-30	PM
ANEX A 552	Aliphatic PU Adhesive	40 ± 2	4	40-60	DMF / TOL/IPA
ANEX INJ 502-30	Aliphatic PU Topcoat for Injection	30 ± 1	50	40-60	Alcohol/Toluene
ANEX 604-30 INJECTION	Aliphatic PU Topcoat for Injection	30 ± 1	50	40-60	Alcohol/Toluene
ANEX INJ 502-200	Aliphatic PU Topcoat for Injection	30 ± 1	200	40-60	Alcohol/Toluene

Being highly versatile, Aromatic Polyurethanes are first choice for most of the flexible coating applications. While aromatic ring structure of hard segments provides excellent mechanical and chemical resistance, still provides outstanding flexibility and offers very cost friendly options. Synthetic leather applications, such as garments, shoes, coagulated polyurethane leather and technical textile applications such as safety wear and medical fabric coating, are some of the important ones of countless Aromatic PU applications.

Topcoat

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX M 028	Aromatic PU	35 ± 1	28	30-50	DMF
ANEX M 030	Aromatic PU	30 ± 1	30	60-90	DMF
PURANEX M 1031/30	Aromatic PU	30 ± 1	30	40-60	DMF
PURANEX M 3030/30	Aromatic PU	30 ± 1	30	40-60	DMF
ANEX M 043S	Aromatic PU	35 ± 1	38	40-60	DMF
PURANEX TM 1040/35	Aromatic PU	35 ± 1	40	70-100	DMF
ANEX M 045	Aromatic PU	30 ± 1	45	50-80	DMF
PURANEX M 3045/30	Aromatic PU	30 ± 1	45	40-60	DMF
ANEX M 050	Aromatic PU	35 ± 1	50	140-180	DMF
ANEX M065	Aromatic PU	30 ± 1	65	30-50	DMF
ANEX M070	Aromatic PU	35 ± 1	70	60-80	DMF
PURANEX M 1070/45	Aromatic PU	45 ± 1	70	15-30	DMF
ANEX M 075	Aromatic PU	30 ± 1	75	60-80	DMF
ANEX M 080	Aromatic PU	29 ± 1	80	50-80	DMF/TOL/MEK
ANEX M 082	Aromatic PU	30 ± 1	80	60-90	DMF
ANEX WF5080	Aromatic PU	35 ± 1	80	70-100	DMF
PURANEX M 1080/30	Aromatic PU	30 ± 1	80	60-80	DMF
PURANEX M 1080/35	Aromatic PU	35 ± 1	80	60-80	DMF
ANEX WF5095	Aromatic PU	35 ± 1	100	70-100	DMF
PURANEX M 3100/35	Aromatic PU	35 ± 1	100	30-50	DMF/TOL
ANEX M102H	Aromatic PU	30 ± 1	102	30-50	DMF
ANEX M 073	Aromatic PU	25 ± 1	140	4-8	DMF/TOL
PURANEX M 1150/25	Aromatic PU	25 ± 1	150	4-8	DMF
PURANEX M 1200/30	Aromatic PU	30 ± 1	200	40-60	DMF
ANEX M 074	Aromatic PU	25 ± 1	230	4-8	DMF/TOL
ANEX M 235	Aromatic PU	30 ± 1	235	50-80	DMF
PURANEX MS 1030/30	Aromatic PU Silky Touch	30 ± 1	30	40-60	DMF
PURANEX TMS 1080/35	Aromatic PU Silky Touch	35 ± 1	80	60-80	DMF
PURANEX MC 1025/30	Aromatic Polycarbonate PU	30 ± 1	25	60-80	DMF
PURANEX MC 1030/30	Aromatic Polycarbonate PU	30 ± 1	30	60-80	DMF
PURANEX MC 1050/35	Aromatic Polycarbonate PU	35 ± 1	50	60-80	DMF
PURANEX MH 1050/50	Aromatic Polycarbonate PU	50 ± 1	50	35-50	DMF
ANEX M 070C	Aromatic Polycarbonate PU	35 ± 1	70	60-90	DMF
ANEX M 801	Aromatic Polycarbonate PU	29 ± 1	80	50-80	DMF/TOL/MEK
DMF-Free&TOL-Free					
PURANEX M 5028/30	Aromatic PU (DMF-Free & TOL-Free)	30 ± 1	28	30-50	DMSO/PMA
ANEX ECO M 030	Aromatic PU (DMF-Free & TOL-Free)	30 ± 1	30	60-90	DMSO/PMA
ANEX ECO M 075	Aromatic PU (DMF-Free & TOL-Free)	30 ± 1	75	60-80	DMSO/PMA
PURANEX TM 5070/30	Aromatic PU (DMF-Free & TOL-Free)	30 ± 1	70	60-80	DMSO/PMA
PURANEX TM 5075/30	Aromatic PU (DMF-Free & TOL-Free)	30 ± 1	75	60-80	DMSO/PMA
PURANEX TM 7080/30	Aromatic PU (DMF-Free & TOL-Free)	29 ± 1	80	50-80	DMP/MEK
ANEX M 086	Aromatic PU (DMF-Free & TOL-Free)	29 ± 1	80	50-80	DMSO,PMA,MEK
ANEX WF 5086	Aromatic PU (DMF-Free & TOL-Free)	35 ± 1	80	70-100	DMSO/PMA/MEK
ANEX M 170C	Aromatic Polycarbonate PU (DMF-Free & TOL-Free)	35 ± 1	70	60-80	PMA/MEK/DMSO
ANEX M 076C	Aromatic Polycarbonate PU (DMF-Free & TOL-Free)	35 ± 1	75	60-90	DMSO/PMA/MEK

Polymers with
High Performance

Adhesive

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX A 540	Aromatic Polyester PU	40 ± 1	N/A	15-30	DMF/TOL/MEK
ANEX A 552	Aromatic Polyester PU	40 ± 1	4	8-15	DMF/TOL/IPA
ANEX A 516	Aromatic Polyester PU	35 ± 1	7	40-60	DMF/TOL/MEK
ANEX A 506	Aromatic Polyester PU	35 ± 1	8	40-60	DMF/TOL
ANEX A 010	Aromatic Polyester PU	43 ± 1	10	50-80	DMF/TOL
ANEX A 526	Aromatic Polyester PU	40 ± 1	20	50-90	DMF/TOL
ANEX A 025	Aromatic Polyester PU	47 ± 2	25	80-120	DMF/TOL
ANEX A 624	Aromatic Polyester PU	47 ± 2	25	15-30	DMF/TOL
PURANEX A 3030/50	Aromatic Polyester PU	50 ± 1	30	40-60	DMF/TOL
ANEX A 013H	Aromatic Polyether PU	35 ± 1	13	30-50	DMF/MEK/TOL
ANEX A 018HM	Aromatic Polyether PU	38 ± 1	18	50-90	DMF/MEK/TOL
ANEX A 018H	Aromatic Polyether PU	40 ± 1	18	50-90	DMF/TOL
PURANEX TAH 3018/45	Aromatic Polyether PU	45 ± 1	18	20-40	DMF/TOL
ANEX A 023H	Aromatic Polyether PU	43 ± 1	25	80-120	DMF/MEK/TOL
PURANEX AH 3030/35	Aromatic Polyether PU	35 ± 1	30	30-50	DMF/TOL/MEK
DMF-Free&TOL-Free					
PURANEX A 5006/35	Aromatic Polyester PU	35 ± 1	6	40-60	PMA/DMSO
PURANEX A 5010/43	Aromatic Polyester PU	43 ± 1	10	50-80	PMA/DMSO
ANEX A 026	Aromatic Polyester PU	46 ± 1	25	80-120	DMSO/PMA/MEK
ANEX A 016H	Aromatic Polyether PU	40 ± 1	18	50-90	DMSO/PMA/MEK
PURANEX TAH 7018/40	Aromatic Polyether PU	40 ± 1	18	50-90	DMP/MEK

Coagulation

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX W 3030	Aromatic Wet Process PU	30 ± 1	30	160-240	DMF
ANEX W 3045	Aromatic Wet Process PU	30 ± 1	45	160-240	DMF
ANEX W 3080	Aromatic Wet Process PU	30 ± 1	80	160-240	DMF
ANEX W 3150	Aromatic Wet Process PU	30 ± 1	150	160-240	DMF
ANEX W 3240	Aromatic Wet Process PU	30 ± 1	240	160-240	DMF
ANEX W 6018	Aromatic Wet Process PU	30 ± 1	18	160-240	DMF
ANEX W2020	Aromatic Wet Process PU	20 ± 1	150	100-140	DMF
ANEX W2080	Aromatic Wet Process PU	20 ± 1	80	100-140	DMF
ANEX W3090	Aromatic Wet Process PU	30 ± 1	90	160-240	DMF
ANEX W3140	Aromatic Wet Process PU	30 ± 1	140	160-240	DMF
WETANEX W 1010/30	Aromatic Wet Process PU	30 ± 1	10	160-240	DMF
WETANEX W 1050/30	Aromatic Wet Process PU	30 ± 1	50	160-240	DMF
WETANEX W 1081/30	Aromatic Wet Process PU	30 ± 1	80	160-240	DMF
WETANEX CW 1010/30	Aromatic Wet Process Polycarbonate PU	30 ± 1	10	160-240	DMF
WETANEX CW 1030/30	Aromatic Wet Process Polycarbonate PU	30 ± 1	30	160-240	DMF
WETANEX CW 1050/30	Aromatic Wet Process Polycarbonate PU	30 ± 1	50	160-240	DMF
WETANEX WH 1025/30	Aromatic Wet Process Polyether PU	30 ± 1	25	160-240	DMF
WETANEX WH 1075/30	Aromatic Wet Process Polyether PU	30 ± 1	75	160-240	DMF
WETANEX WH 1085/30	Aromatic Wet Process Polyether PU	30 ± 1	85	160-240	DMF

Hot Stamping Coagulation for Agenda and Label Leathers

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
WETANEX W 1035/30 ST	Aromatic Wet Process PU for Hot Stamping	30 ± 1	35	160-240	DMF
WETANEX W 1050/35ST	Aromatic Wet Process PU for Hot Stamping	35 ± 1	50	160-240	DMF
ANEX W 108K	Aromatic Wet Process PU for Hot Stamping	30 ± 1	65	160-240	DMF
ANEX W 3534 ST	Aromatic Wet Process PU for Hot Stamping	35 ± 1	100	90-140	DMF
ANEX W 5120 ST	Aromatic Wet Process PU for Hot Stamping	35 ± 1	120	180-240	DMF
ANEX W 5200 ST	Aromatic Wet Process PU for Hot Stamping	35 ± 1	220	160-240	DMF

PU Glove by Coagulation

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
WETANEX GL 1010/30	PU Resin for Glove Production	30	10	160-240	DMF
WETANEX GLH 1025/30	PU Resin for Glove Production	30	25	120-180	DMF
WETANEX GL 1030/30	PU Resin for Glove Production	30	30	160-240	DMF
WETANEX GL 1035/25	PU Resin for Glove Production	25	35	140-180	DMF
WETANEX GL 1045/25	PU Resin for Glove Production	25	45	140-180	DMF
WETANEX GL 1050/30	PU Resin for Glove Production	30	50	140-180	DMF
WETANEX GL 5030/25	PU Resin for Glove Production (Touch Screen)	25	30	140-180	DMF
WETANEX GL 5030/30	PU Resin for Glove Production (DMF-Free)	30	30	160-240	DMSO
WETANEX GL 7030/30	PU Resin for Glove Production (DMF-Free)	30	30	160-240	DMP

High Solid Polyurethane

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX HS 108	High Solid PU	100 ± 1	11	60-90	-
ANEX HS 112	High Solid PU	100 ± 1	12	60-90	-
ANEX HS 118	High Solid PU	96 ± 1	18	60-90	-
ANEX D 80	Curing Agent for High Solid PU	100 ± 1	N/A	0,1	-
ANEX E 43	Foaming Agent for High Solid PU	50 ± 1	N/A	5-10	DOTP

Polyurethane for Bronzing Textiles

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX M 5045	PU Resin for Bronzing Textile	30%	40-50	60-90	DMF
ANEX BA 7048	PU Resin for Bronzing Textile	50%	40-50	70-110	DMF/TOL/EAC
ANEX M 061	PU Resin for Bronzing Textile	67%	50-60	100-150	DMF/TOL/MEK
ANEX M 5050	PU Resin for Bronzing Textile	50%	40-50	100-140	DMF/TOL/MEK

Polyurethane for Textile Lamination

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX M 5068	PU Resin for Textile Lamination	70%	N/A	140-180	DMF/TOL/MEK

Polyurethane for Textile Lamination

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
PURANEX BM 3001/60	PU Resin for Foil Transfer	60%	N/A	40-60	DMF/TOL/MEK

Polyurethane for Hook & Loop

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
PURANEX TA 3000/35	PU Resin for Hook & Loop	35	N/A	0,1 - 0,3	DMF/TOL/MEK

AROMATIC POLYURETHANE RESIN

Fashion Meets
Technology

In the world of fashion, appearance and the touch of a leather are the aspects where most of the added value is generated. A good range of finishing materials promote creativity without compromising performance. Our lacquers and finishing resins are developed to rule out the limitations on designing process, nurturing artistic expressions of coating technics and becoming the path way to new trends.

Gloss & Matt Finish

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX LR 340	Gloss Finish	21 ± 1	N/A	1500-2000	IPA/TOL
ANEX LR 340 C	Gloss Finish	20 ± 1	N/A	1000-4000	IPA/TOL
ANEX LR 144	Super Gloss Resin	35 ± 1	N/A	1000-3000	DMF/MEK
ANEX LR 342	Aliphatic Matt Finish	17 ± 1	N/A	400-1500	IPA/TOL
CREANEX L 555	Aliphatic Matt Finish	20 ± 1	N/A	700-2500	Alcohol
CREANEX L 706	Aliphatic Matt Finish	17 ± 1	N/A	300-700	Alcohol/Tol
CREANEX L 796	Aliphatic Matt Finish	13 ± 1	N/A	300-700	Alcohol/Tol
CREANEX L 565	Aliphatic Matt Finish	20 ± 1	N/A	700-2500	Alcohol
CREANEX LC 175/A	Aliphatic Matt Finish DMF-Free	15 ± 1	N/A	1500-2000	DAA/PM
ANEX LR 142A	Aromatic Deep Matt Finish	19 ± 1	N/A	600-1800	DMF/MEK
CREANEX M 142/15	Aromatic Matt Finish	15 ± 1	N/A	50-350	DMF/MEK
CREANEX M 142/H	Aromatic Matt Finish	18 ± 1	N/A	500-100	DMF/MEK
CREANEX M 401	Aromatic Matt Finish	13 ± 1	N/A	500-2000	DMF / MEK
CREANEX M 796	Aromatic Matt Finish	13 ± 1	N/A	500-1000	MEK/TOL
ANEX LR 106	Deep Matt Finish	20 ± 1	N/A	300-1500	IPA/TOL
ANEX LR 135A	High Solid Matt Finish	35 ± 1	N/A	5000-20000	DMF, TOL
ANEX LR 108	Matt Finish	17 ± 1	N/A	45-100	IPA/TOL
CREANEX L 103	Matt Finish DMF-Free	17 ± 1	N/A	200-1500	TOL/PM/IPA
ANEX LR 166	Matt Resin for Reverse Roll	23 ± 1	N/A	25000-50000	MEK/TOL/PM/DMF
ANEX LR 175A	Polycarbonate Matt Finish	15 ± 1	N/A	200-1000	IPA/TOL

Touch Feeling Finish

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX LR 596	Aliphatic Matt Oil Finish	17 ± 1	N/A	300-1500	IPA/TOL
ANEX LR 513	Aliphatic Matt Waxy Finish	16 ± 1	N/A	100-800	IPA/TOL/DMF
ANEX LR 574	Aliphatic Matt Waxy Silky Finish	17 ± 1	N/A	300-1000	DMF/TOL/IPA
ANEX LR 1524	Aromatic Waxy Finishing for Sofa	22 ± 1	N/A	700-3000	DMF/TOL/BG/MEK
ANEX LR 605	Fuzzy Resin	30 ± 1	N/A	3000-8000	DMF
ANEX LR 652	Gloxx Waxy Aliphatic Finish	17 ± 1	N/A	200-1000	DMF/TOL/MEK
ANEX LR 1507	Grippy Finish	19 ± 1	N/A	1000-1500	DMF / MEK / TOL
ANEX LR 1508	Grippy Finish	19 ± 1	N/A	500-2000	DMF/MEK/TOL
ANEX LR 1581/D	Matt Finish	18 ± 1	N/A	300-1000	DMF/MEK/TOL
ANEX LR 548/C	Matt Grippy Finish	21 ± 1	N/A	200-800	MEK/DMF/TOL
ANEX LR 1671	Matt Waxy Heat Resistant Finishing	20 ± 1	N/A	300-1500	DMF/MEK/TOL
ANEX LR 1681/T	Matt Wet Waxy Finish	18 ± 1	N/A	300-1000	DMF/MEK/TOL
ANEX LR 1681-T DMF FREE	Matt Wet Waxy Finishing DMF-Free	18 ± 1	N/A	300-1000	MEK/TOL
ANEX LR 525	Skin Touch Finish	22 ± 1	N/A	1000-4000	MEK/DMF/TOL
ANEX LR 525 DMF FREE	Skin Touch Finish DMF-Free	22 ± 1	N/A	600-25000	TOL/MEK
ANEX LR 158/N	Soft Aromatic Matt Finish	18 ± 1	N/A	1000-1500	DMF/MEK/TOL
ANEX LR 622	Soft Fuzzy Resin	30 ± 2	N/A	4000-7000	DMF/TOL/PM
CREANEX M 424	Soft Touch Matt Finish	19 ± 1	N/A	500-1000	DMF/MEK
CREANEX M 597	Soft Touch Matt Finish	19 ± 1	N/A	200-1000	DMF/MEK
CREANEX M 344/25	Super Gloss Fast Drying Finishing	25 ± 1	N/A	500-1500	DMF/MEK
ANEX LR 1650/V	Touch Finish	21 ± 1	N/A	500-2000	DMF/MEK/TOL
CREANEX LS 510	Touch Finish	28 ± 1	N/A	5000-8000	IPA/TOL/DMF
CREANEX LS 530	Touch Finish	28 ± 1	N/A	750-2500	IPA/TOL
CREANEX M 154/15	Touch Finish	15 ± 1	N/A	30-100	DMF/MEK
ANEX LR 1506	Wet Waxy Finish	17 ± 1	N/A	1000-1500	DMF/MEK/TOL
ANEX LR 623/T	Wet Waxy Smooth Finishing	17 ± 1	N/A	300-1000	DMF/MEK/TOL

Yangbuck Resin

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX LR 732	Flesher Yangbuck	20 ± 1	N/A	4000-20000	TOL/MEK
ANEX LR 2785	Medium Aliphatic Yangbuck	20 ± 1	N/A	10000-20000	TOL/PM
ANEX LR 2785N	Medium Aliphatic Yangbuck	20 ± 1	N/A	7000-20000	TOL/PM
ANEX LR 2787	Medium Aliphatic Yangbuck	21 ± 1	N/A	7500-20000	PM/TOL
ANEX LR 1766/A	Medium Yangbuck	24 ± 1	N/A	2000-10000	MEK/PM/BG
ANEX LR 731M	New Flesher Yangbuck	20 ± 1	N/A	1500-4000	TOL/MEK
ANEX LR 726N	New Medium Yangbuck	17 ± 1	N/A	750-2500	EAC/BG
ANEX LR 729M	New Medium Yangbuck	19 ± 1	N/A	1500-4000	TOL/MEK
ANEX LR 2998	Rough Yangbuck	35 ± 2	N/A	4000-12000	TOL/MEK
ANEX LR 1766	Rough Yangbuck	21 ± 1	N/A	2000-7000	MEK/PM/BG
ANEX LR 746	Rough Yangbuck Resin	25 ± 1	N/A	8000-18000	EAC/MEK
ANEX LR 1752/A	Waxy Medium Yangbuck	30 ± 2	N/A	5000-15000	TOL/MEK
ANEX LR 1752/A DMF FREE	Waxy Medium Yangbuck DMF-Free	34 ± 1	N/A	5000-20000	PM/TOL
ANEX LR 1752	Waxy Rough Yangbuck	29 ± 1	N/A	5000-27000	MEK/TOL
ANEX LR 1752 DMF FREE	Waxy Rough Yangbuck DMF-Free	28 ± 1	N/A	5000-20000	PM/TOL
ANEX LR 1592/Y	Waxy touch Yangbuck	23 ± 1	N/A	200-600	DMF/TOL/MEK
CREANEX M 701 DMF FREE	Yangbuck DMF-Free	24 ± 1	N/A	3000-10000	MEK
CREANEX M 731M DMF FREE	Yangbuck DMF-Free	19 ± 1	N/A	1500-4000	PM/TOL
CREANEX M 739 DMF FREE	Yangbuck DMF-Free	22 ± 1	N/A	3000-5000	PM/TOL
CREANEX M 1752 DMF-TOL FREE	Yangbuck DMF-TOL-Free	31 ± 1	N/A	10000-20000	PM/IPA
ANEX LR 764	Yangbuck Finish	39 ± 1	N/A	7000-10000	IPA/TOL

Special Finish

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX LR 9200	Anti Scratch Finish	16 ± 1	N/A	1500-2500	DMF/TOL
CREANEX M 9200/30	Anti Scratch Finish	30 ± 1	N/A	1000-4000	DMF/MEK
ANEX LR 956/N	Burnish Finish	26 ± 1	N/A	1000-2000	DMF/TOL
ANEX LR 947	Dark Burnish Finish	23 ± 1	N/A	100-800	DMF/TOL/BG/CYC
ANEX BLACK 163	Carbon Black Finish Injection	26 ± 1	N/A	200-600	DMF/MEK/TOL
ANEX BLACK 186-5	Carbon Black Finish	34 ± 2	N/A	2000-5500	DMF/MEK/TOL/EAC
ANEX BLACK 186-5 DMF FREE	Carbon Black Finish DMF-Free	36 ± 2	N/A	2000 - 5500	PM/TOL/EAC/DAA
ANEX BLACK 186-5B	Carbon Black Finish	34 ± 2	N/A	2000-5500	IPA/DMF/TOL/DAA/EAC/PM
ANEX BLACK 189	Carbon Black Finish	36 ± 2	N/A	800-1500	DMF/MEK/TOL
CREANEX M 838	Crazy Horse White	29 ± 2	N/A	6000-10000	TOL
ANEX LR 826B	Crazy Horse Black	30 ± 1	N/A	8000-10000	BAC/MEK/TOL
ANEX LR 838/Y	Crazy Horse Yellow	32 ± 1	N/A	6000-8000	BAC/MEK/TOL
ANEX LR 115F	Foil Adhesive	20 ± 1	N/A	400-1500	IPA/TOL
ANEX LR 1530	Hot Stamp	25 ± 1	N/A	700-3000	DMF/TOL/BG/MEK
ANEX LR 1946R	Hot Stamp	37 ± 2	N/A	4000-8000	DMF
ANEX LR 1946W	Hot Stamp	35 ± 2	N/A	4000-8000	DMF/MEK/TOL
ANEX INJECTION	Injection Gloss Finish	15 ± 1	N/A	150-600	DMF/TOL/MEK
CREANEX L 133	Injection Matt Finish	13 ± 1	N/A	100-500	IPA/TOL/PM
ANEX LR 103	Injection Matt Finish	15 ± 1	N/A	1000-3000	IPA/TOL/PM
ANEX LR 118/A	Injection Matt Finish	17 ± 1	N/A	400-1200	DMF/TOL/MEK
ANEX LR 143	Injection Matt Finish	16 ± 1	N/A	250-800	DMF/TOL/IPA
ANEX LR 161/A	Injection Matt Finish	19 ± 1	N/A	1500-2500	IPA/TOL
ANEX LR 181/B	Injection Matt Finish	15 ± 1	N/A	250-1000	TOL/PM/IPA
ANEX LR 181A	Injection Matt Finish	14 ± 1	N/A	300-1000	IPA/TOL/Glycol Ethers
ANEX LR 955	Polish Finish	18 ± 1	N/A	500-1500	IPA/TOL
ANEX LR 921/C	Polish Finish	19 ± 1	N/A	3000-8000	Water
ANEX LR 181/B	Injection Matt Finish	15 ± 1	N/A	250-1000	TOL/PM/IPA
ANEX LR 181A	Injection Matt Finish	14 ± 1	N/A	300-1000	IPA/TOL/Glycol Ethers
ANEX LR 955	Polish Finish	18 ± 1	N/A	500-1500	IPA/TOL
ANEX LR 921/C	Polish Finish	19 ± 1	N/A	3000-8000	Water
ANEX LR 181/B	Injection Matt Finish	15 ± 1	N/A	250-1000	TOL/PM/IPA
ANEX LR 181A	Injection Matt Finish	14 ± 1	N/A	300-1000	IPA/TOL/Glycol Ethers
ANEX LR 955	Polish Finish	18 ± 1	N/A	500-1500	IPA/TOL
ANEX LR 921/C	Polish Finish	19 ± 1	N/A	3000-8000	Water
ANEX NEW PULL-UP	Pull-Up Finish	27 ± 2	N/A	4000-12000	DMF/MEK
ANEX PL 103 PULL UP	Pull-Up Finish	36 ± 2	N/A	10000-15000	DMF/MEK/EAC
ANEX PL 131	Pull-Up Finish	28 ± 1	N/A	5000-1400	DMF/MEK

Vinyl Acrylic Finish

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
LACANEX 375	Acrylic for Coating	24 ± 1	N/A	100-500	MEK/DAA
LACANEX 370	Acrylic for Coating	21 ± 1	N/A	50-500	TOL-MEK
INTER 329/25	Acrylic for Coating	24 ± 1	N/A	2000-4500	DMF/MEK/TOL
LACANEX 337/33 HV	Acrylic For Coating	35 ± 1	N/A	14000-20000	DMF/TOL/MEK
INTER 330/25D	Acrylic For Coating	25 ± 1	N/A	200-1000	DMF/MEK/TOL
LACANEX 526 HV	Acrylic For Coating DMF-Free	22 ± 1	N/A	1000-4000	MEK/EAC
LACANEX 537	Acrylic For Coating DMF-Free	26 ± 1	N/A	1000-2500	MEK/EAC
LACANEX 505	Acrylic for Coating- DMF-Free	21 ± 1	N/A	2000-5000	MEK/TOL
LACANEX 500	Acrylic For Coating DMF-TOL-Free	20 ± 1	N/A	300-600	MEK/PM
INTER 308/20	Acrylic Touch Finish	20 ± 1	N/A	200-1000	DMF/MEK/TOL
INTER 328/25	Acrylic Touch Finish DMF-TOL-Free	26 ± 1	N/A	10000-20000	MEK/BAC/PM
ANEX LR 2558	Agenda Touch Finish	21 ± 1	N/A	100-500	DMF/TOL/BAC
ANEX LR 2555	Agenda Touch Finish	25 ± 1	N/A	10-100	DMF/TOL/BAC
ANEX LR 2555A	Agenda Touch Finish	25 ± 1	N/A	10-100	BAC/TOL/EAC
ANEX LR 2995A	Brush-Off	20 ± 1	N/A	250-700	TOL/MEK/EAC
ANEX LR 2995B	Brush-Off Agent	6 ± 1	N/A	N/A	N/A
ANEX LR 955K	Burnish Acrylic Finish	24 ± 1	N/A	100-700	EAC/TOL/CYC/MEK/PM
ANEX LR 952	Burnish Acrylic Finish	28 ± 1	N/A	400-1200	DMF/MEK
ANEX LR 953/T	Burnish Acrylic Finish	29 ± 1	N/A	15000-45000	MEK/DMF/TOL
INTER 115/A	Copolymer Finish	15 ± 1	N/A	50-400	MEK
ANEX LR 383/A	Crack Finish	35 ± 1	N/A	15000-30000	DMF/MEK
ANEX LR 383	Crack Finish	34 ± 1	N/A	8000-18000	BAC/EAC/PM
ANEX LR 385	Crack Finish	50 ± 2	N/A	15.000-30.000	DMF/MEK
ANEX LR 387	Crack Finish	25 ± 1	N/A	3000-6000	DMF/MEK/TOL
ANEX LR 173/A	Easy Clean Finish DMF-Free	19 ± 1	N/A	100-500	MEK/EAC/BG
ANEX LR 176	Easy Clean Finish	17 ± 1	N/A	80-200	DMF/MEK
ANEX LR 176/A	Easy Clean Finish	18 ± 1	N/A	50-400	DMF/MEK
ANEX LR 145F	Foil Protection Finish	36 ± 2	N/A	100-750	TOL/BAC
LACANEX 380	Gloss Acrylic Finish	25 ± 1	N/A	1500-2000	DMF/MEK/TOL
LACANEX 900	Gloss Acrylic Finish	25 ± 1	N/A	700-2000	DMF/MEK/TOL
LACANEX 321	Gloss Acrylic Finish	37 ± 1	N/A	100-500	DMF/MEK
ANEX LR 1350A	Gloss Acrylic Finish	23 ± 1	N/A	200-1000	DMF/TOL/MEK/BG
INTER 300/25 E	Gloss Acrylic Finish	25 ± 1	N/A	700-2000	DMF/MEK/TOL
ANEX LR 610	Gloss Acrylic Finish	23 ± 1	N/A	800-1500	DMF/MEK/TOL
INTER 326/25	Gloss Acrylic Finish DMF-TOL-Free	25 ± 1	N/A	9000-18000	MEK/BAC/PM
LACANEX 355	Matt Acrylic Finish	49 ± 1	N/A	500-2000	DMF/MEK/TOL
INTER 305/25 E	Matt Acrylic Finish	21 ± 1	N/A	4500-6000	DMF/MEK/TOL
ANEX LR 617	Matt Acrylic Finish	25 ± 1	N/A	800-1500	DMF/MEK/TOL
LACANEX 905	Matt Vinyl Acrylic Finish	21 ± 1	N/A	4500-6000	DMF/MEK/TOL
LACANEX 106	Semi Gloss Acrylic Finish	20 ± 1	N/A	300-500	DMF/TOL/MEK
LACANEX 809/18	Semi Matt Acrylic Finish	18 ± 1	N/A	200-500	MEK/DAA
LACANEX 606	Waxy Agenda Finish DMF-TOL-Free	28 ± 1	N/A	30	MEK

Acrylic Lacquer for Tarpaulin

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
INTER 215	Gloss Tarpaulin Finish	17 ± 1	N/A	1000-5000	EAC/DAA/TOL/MEK/DMF/PM/IPA
INTER 216	Gloss Tarpaulin Finish	17 ± 1	N/A	1000-3000	DMF/MEK/TOL
INTER 270	Gloss Tarpaulin Finish	18 ± 1	N/A	100-500	DMF/MEK/TOL
INTER 208/19	Gloss Tarpaulin Finish	19 ± 1	N/A	100-400	DMF/MEK/TOL
INTER 213	Gloss Tarpaulin Finish	20 ± 1	N/A	1000-4000	DMF/MEK/TOL
INTER 210	Gloss Tarpaulin Finish	20 ± 1	N/A	1000-2400	DMF/MEK/TOL
INTER 115	Gloss Tarpaulin Finish	15 ± 1	N/A	50-400	MEK
INTER 207/19	Gloss Tarpaulin Finish	19 ± 1	N/A	200-700	DMF/MEK/TOL
INTER 212/19S	Gloss Tarpaulin Finish	19 ± 1	N/A	200-800	DMF/MEK/TOL
INTER 232	Matt Tarpaulin Finish	25 ± 1	N/A	5000-40000	DMF/MEK/TOL
INTER 225	Silver Tarpaulin Finish	24 ± 1	N/A	1000-3000	DMF/MEK/TOL
INTER 225/19S	Silver Tarpaulin Finish	19 ± 1	N/A	50-300	DMF/MEK/TOL
INTER 256	Tarpaulin Finish	19 ± 1	N/A	300-500	DMF/MEK/TOL
INTER 265	Tarpaulin Finish	19 ± 1	N/A	300-700	DMF/MEK/TOL
INTER 214	Tarpaulin Finish	20 ± 1	N/A	3000-8000	DMF/MEK/TOL
INTER 218	Tarpaulin Finish	20 ± 1	N/A	500-2000	MEK/TOL/PM/IPA/CYC
INTER 260	Tarpaulin Finish	21 ± 1	N/A	300-700	DMF/MEK/TOL
INTER 212	Tarpaulin Finish	22 ± 1	N/A	1000-3000	DMF/MEK/TOL
INTER 211	Tarpaulin Finish	18 ± 1	N/A	800-1500	DMF/MEK/TOL
LACANEX 804/15	Tarpaulin Finish DMF-TOL Free	15 ± 1	N/A	100-300	GBL-MEK

ADDITIVES

Product Name	Description	Solid (%)	Modulus 100% (kg/cm ²)	Viscosity (Pa.s)	Solvent
ANEX S 100	Levelling Agent	99 ± 1	N/A	0,5-1,5	-
ANEX AE 090	PVC Crosslinking Plasticizer	99 ± 1	N/A	N/A	-
ANEX SIL 145C	Slippery Agent	7 ± 1	N/A	N/A	DMF
Crosslinking					
ANEX C98	Aliphatic Polyisocyanate Crosslinker	80 ± 1	N/A	N/A	EPA
ANEX C1	Aromatic Polyisocyanate Crosslinker	75 ± 1	N/A	1,5-2,5	EAC
ANEX C1B	Aromatic Blocked Polyisocyanate Crosslinker	50 ± 1	N/A	8-12	EAC
ANEX C2	Aromatic Melamine Crosslinker	80 ± 1	N/A	N/A	IBA
ANEX A1	Accelerator for Anex C1	2 ± 0,1	N/A	N/A	EAC
ANEX A6	Accelerator for Anex C2	10 ± 0,2	N/A	N/A	DMF
Coagulation					
ANEX S 11	Anionic Additive	89 ± 1	N/A	N/A	Water
ANEX S 80	Non-ionic Additive	87 ± 1	N/A	N/A	Water
ANEX DEFOAMER	Defoaming Agent	99 ± 1	N/A	N/A	N/A
ADDANEX WS 003	DMF Exchange Promoter	99 ± 1	N/A	N/A	N/A
ADDANEX WS 090	Levelling and Wetting Agent	99 ± 1	N/A	N/A	N/A
Thumbling					
ANEX 8215	Slippery Additive for Thumbling	14 ± 1	N/A	0,01 - 0,05	Water
ANEX 8218	Softening Additive for Thumbling	29 ± 1	N/A	0,01 - 0,02	Water
Matting Agents					
ADDANEX MA 001	Matting Agent	20 ± 1	N/A	N/A	Glycol Ether
ADDANEX MA 002	Matting Agent	20 ± 1	N/A	N/A	Glycol Ether



by interplast
ANEX
your partner in chemistry

İTERPLAST KİMYA SAN. ve TİC. A.Ş.
Değirmenköy Fevzipaşa Mahallesi Erdoğan Sokak No:5
Silivri / İstanbul - TURKEY

T: +90 (212) 346 09 29 (pbx)
F: +90 (212) 346 09 99
E: info@interplastkimya.com